

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08J 7/02, C08C 3/02, B01D 11/02		A1	(11) International Publication Number: WO 97/38044
			(43) International Publication Date: 16 October 1997 (16.10.97)
(21) International Application Number: PCT/GB97/01009		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 9 April 1997 (09.04.97)		Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(30) Priority Data: 9607399.4 10 April 1996 (10.04.96) GB			
(71) Applicant (for all designated States except US): BESPAC PLC [GB/GB]; Bergen Way, North Lynn Industrial Estate, King's Lynn, Norfolk PE30 2JJ (GB).			
(72) Inventor; and (75) Inventor/Applicant (for US only): BARNES, Paul [GB/GB]; 15 Graham Drive, Fair Green, Middleton, King's Lynn, Norfolk, PE32 1RL (GB).			
(74) Agent: BOULT WADE TENNANT; 27 Furnival Street, London EC4A 1PQ (GB).			
(54) Title: A METHOD OF CLEANING OR PURIFYING ELASTOMERS AND ELASTOMERIC ARTICLES WHICH ARE INTENDED FOR MEDICAL OR PHARMACEUTICAL USE			
(57) Abstract <p>A method of cleaning or purifying elastomers and elastomeric articles which are intended for medical or pharmaceutical use which method comprises firstly performing a solvent extraction process on the elastomer or elastomeric article using a solvent in a non-supercritical state to substantially remove impurities therefrom and thereafter subjecting the elastomer or elastomeric article to a further solvent extraction step using a supercritical fluid or a mixture of supercritical fluids in order to remove or substantially reduce the concentration of the residue of extracting solvent remaining in the elastomer or elastomeric article after the first solvent extraction process.</p>			

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**A METHOD OF CLEANING OR PURIFYING ELASTOMERS AND
ELASTOMERIC ARTICLES WHICH ARE INTENDED FOR MEDICAL OR
PHARMACEUTICAL USE**

5 This invention relates to a method of cleaning or
purifying elastomers and elastomeric articles which in
particular are intended for medical or pharmaceutical
uses but also for cleaning or purifying elastomers and
elastomeric articles for any use in which impurities
10 in the elastomer might cause problems through leaching
or extraction into the adjacent media.

 Pressurised metered dose inhalers [MDIs] have
been available over the last thirty years for the
administration of medicaments or drugs, primarily to
15 the lungs, for the treatment of asthma and other
airway diseases. Additionally, they have been used
for the administration of drugs to the lung for
systemic absorption, for administration to the oral
cavity and for administration into the nose. All of
20 these pressurised inhalers utilise aerosol valves that
meter individual doses. These metering valves are
constructed of a mixture of metal and/or plastic parts
and elastomeric rubbers. Various types of elastomeric
rubber are used in these valves and newer types are
25 being continually developed to ensure compatibility
with the various aerosol propellants, to provide
compatibility with and stability of the drug
formulation and to ensure that the valve continues to
perform to specification over the several years of
30 storage required of a pharmaceutical product. One
consequence of this protracted storage of aerosol
packs in which the propellants are in intimate contact
with the metering valve is that materials are leached
or extracted from the elastomeric rubbers into the
35 drug formulation. These materials which may be

- 2 -

extracted from the elastomeric rubbers are a mixture of the chemical ingredients originally used to make the rubber and also new chemicals produced during the vulcanisation of the rubber. These are undesirable in the finished rubber component as they may cause instability of the formulation and/or degradation of the drug substance and therefore loss of potency, or they may impart objectionable tastes or odours to the product and could in extreme cases cause allergic or toxic reactions.

Both the pharmaceutical manufacturers and the valve manufacturers have been aware of the above problems associated with the use of elastomeric rubber compounds and various approaches have been employed to reduce the extractable chemical materials contained in the rubbers. The main approaches have been to formulate rubbers that will provide a lower level of extractable chemical materials or to pre-extract the rubbers before assembly into the metering valve. Because the final intended use of the product is for administration of drugs, the choice of extraction solvent which can be used is very limited for safety and toxicity reasons as there will remain in the rubber after solvent extraction a residue of this solvent which will be extracted into the propellant system. For this reason the most common extraction solvent used to pre-extract rubbers is the chlorofluorocarbon Trichlorofluoromethane [CCl_3F] which is included as part of the propellant system in a number of MDIs. Trichlorofluoromethane has a boiling point of 23.8°C and is often called Propellant 11 which is abbreviated to P11. Due to its boiling point the liquid can generally be used at ambient temperatures.

This pre-extraction has been carried out by a

- 3 -

variety of methods ranging from soaking the rubbers in P11 with or without stirring, pumping the P11 through a bed of the rubber components to sophisticated custom-designed extraction apparatus where the material extracted from the rubber is continually removed and the rubber continually provided with a stream of pure P11. These methods generally take several days to achieve extraction although extraction is not complete. The processes are intended to reduce the levels of available extractable chemical materials and it is appreciated that they will not be completely eliminated.

More recently the process known as super critical fluid extraction, SCF extraction, has been developed as a general method of extraction for a variety of materials either to remove impurities or to isolate particularly desired chemical compounds.

In WO93/12161 there is described and claimed a method for cleaning elastomeric articles, in particular components for MDIs comprising extracting phthalates and/or polynuclear aromatic hydrocarbons (PAHs) from the articles by contacting the articles with a supercritical fluid. However, a disadvantage of the use of SCFs is that the choice of SCFs which can be used is limited by pressure and temperature considerations as well as toxicity characteristics because residues of the SCF could remain in the rubber after SCF treatment. Thus for practical purposes SCF extraction is mainly limited to the use of carbon dioxide (CO_2) and probably a small number of other chemicals such as nitrous oxide (N_2O).

Likewise, traditional rubber extraction solvents have also been limited by toxicity consideration in view of the residual solvent remaining in the rubber after extraction, and for practical purposes the

- 4 -

choice has usually been between P11, ethanol, ethanol/water mixture and water and a small number of other possibilities.

5 However, it would be useful if it were possible to use other solvents which, although prevented by toxicity considerations from use in hitherto known rubber extraction procedures may have particularly favourable solvent properties for certain of the impurities occurring in the rubbers.

10 According to the present invention there is provided a method of cleaning or purifying elastomers and elastomeric articles which are intended for medical or pharmaceutical use which method comprises firstly performing a solvent extraction process on the
15 elastomer or elastomeric article using a solvent in a non-supercritical state to substantially remove impurities therefrom and thereafter subjecting the elastomer or elastomeric article to a further solvent extraction step using a supercritical fluid or a
20 mixture of supercritical fluids in order to remove or substantially reduce the concentration of the residue of extracting solvent remaining in the elastomer or elastomeric article after the first solvent extraction process.

25 It should be understood that the supercritical fluid used in the present invention is not itself employed to remove impurities in the elastomer but rather to remove or substantially reduce the residue of extracting solvent which has been used previously
30 to remove these impurities. Thus it will be seen that the present invention *inter alia* enables the use for the initial extraction of impurities of extracting solvents would not meet the appropriate toxicity requirements if they left significant residues in the
35 rubber after treatment, and if these residues were not

subsequently removed as in the present invention. Thus, for example, in addition to the conventional extracting solvents of which examples are referred to above, acetone could be used in the method of the present invention as an extracting solvent in the first extraction stage.

The primary characteristics of the SCFs used in the method of the present invention are firstly that they should be safe for use with humans, secondly that they should have a sufficiently low critical temperature, ideally less than 100°C, for practical considerations, and thirdly they should also be good extractants for the solvent or solvents used in the first stages of the method but not necessarily for the original impurities in the rubber which will of course have been already substantially extracted by the solvent used in the first stage of the method.

The actual practical procedures and apparatus for performing the method of the present invention are conventional, the first stage of the method being substantially as has been practised hitherto in conventional extraction-purification procedures for elastomers intended for medical and pharmaceutical use, whilst the second stage of the method employs procedures and apparatus which are conventional in the handling of supercritical fluid extractions, the selection of appropriate conditions, temperatures, pressures and timing of treatment being within the skill of the art.

Following are three outline examples of the method of the present invention.

Example 1

An elastomeric rubber component for an MDI is extracted by soaking in P11 for 3 days. The P11 is

- 6 -

then drained away and the rubber components allowed to air dry. The residual and variable amount of P11 remaining in the extracted rubber is reduced by SCF extraction using Nitrous Oxide for 4 hours.

5

Example 2

Elastomeric rubber components for MDIs are extracted using ethanol for 48 hours. After this period the liquid ethanol is drained off and more of the ethanol is removed from the rubbers by air drying *in situ*. Following this the residual ethanol in the rubbers is further reduced by SCF extraction using Carbon Dioxide at 50°C for 4 hours.

10

Example 3

Rubber components for MDIs are extracted by reflux with acetone at its boiling point of 56.5°C for 24 hours. The acetone containing the extractables is drained away and the rubber components oven dried at 60°C for 6 hours. Residual acetone in the components is removed using SCF extraction with Carbon Dioxide.

15
20

CLAIMS:

1. A method of cleaning or purifying elastomers and elastomeric articles which are intended for
5 medical or pharmaceutical use which method comprises firstly performing a solvent extraction process on the elastomer or elastomeric article using a solvent in a non-supercritical state to substantially remove
10 impurities therefrom and thereafter subjecting the elastomer or elastomeric article to a further solvent extraction step using a supercritical fluid or a mixture of supercritical fluids in order to remove or substantially reduce the concentration of the residue of extracting solvent remaining in the elastomer or
15 elastomeric article after the first solvent extraction process.

2. A method as claimed in claim 1 wherein the
20 supercritical fluid is carbon dioxide (CO₂).

3. A method as claimed in claim 1 or claim 2 wherein the solvent used in the first extraction
process is one or comprises one which is too toxic to be employed in a conventional extraction of impurities
25 but whose residues are reduced to a level of acceptable toxicity by the supercritical fluid extraction step of this method.

4. A method as claimed in claim 3 wherein the
30 solvent used in the first extraction process is a ketone, for example acetone.

5. A method as claimed in any one of claims 1
to 3 wherein the solvent used in the first extraction
35 is an aliphatic alcohol.

6. A method as claimed in any one of claims 1 to 3 wherein the solvent used in the first extraction is a partially or fully halogenated alkane.

5 7. A method as claimed in any one of claims 1 to 3 wherein the solvent used in the first extraction is a polyhydric alkane.

10 8. A method of cleaning or purifying elastomers and elastomeric articles which are intended for medical or pharmaceutical use and which have already been subjected to a solvent extraction process using a solvent in a non-supercritical state to remove
15 impurities therefrom, which method comprises removing or substantially reducing the solvent residue from the solvent extraction process remaining in the elastomer or elastomeric article by extraction with a
20 supercritical fluid or a mixture of supercritical fluids.

25 9. Use of a supercritical fluid or a mixture of supercritical fluids to remove or substantially reduce the concentration of the residue of a solvent in an elastomer or elastomeric article intended for medical
30 or pharmaceutical use which solvent has been used in a non-supercritical state to extract impurities from said elastomer or elastomeric article.

30

35

INTERNATIONAL SEARCH REPORT

Internat. Application No.

PCT/GB 97/01009

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 6 C08J7/02 C08C3/02 B01D11/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
 IPC 6 C08J C08C B01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 417 768 A (SMITH JR CHARLES W ET AL) 23 May 1995 see abstract; claims see column 4, line 38 - column 6, line 11 ---	1-9
Y	US 5 481 058 A (BLACKWELL JOHN A ET AL) 2 January 1996 see abstract; claims; example 9 see column 3, line 28 - column 4, line 49 ---	1-9
A	WO 94 13733 A (VALOIS SA ;TCHEREVATCHENKOFF ANDRE (FR); PERRE CHRISTIAN (FR)) 23 June 1994 see abstract; claims; examples -----	

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 July 1997

Date of mailing of the international search report

21.08.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Mettler, R-M

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 97/01009

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5417768 A	23-05-95	US 5509431 A	23-04-96
US 5481058 A	02-01-96	CA 2180676 A	13-07-95
		EP 0738288 A	23-10-96
		WO 9518834 A	13-07-95
WO 9413733 A	23-06-94	FR 2699544 A	24-06-94
		DE 69309103 D	24-04-97
		EP 0674679 A	04-10-95
		JP 8506046 T	02-07-96

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☒ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.